




DIMENSIONAL TABLE



Size b mm	W.T. s mm	Linear mass Kg/m	Cross-section- al area A cm ²	Second moment of area I cm ⁴	Radius of gyration i cm	Elastic section modulus W cm ³	Torsional inertia constant J cm ⁴	Torsional modulus constant C cm ³
60	3,2	5,62	7,16	38,20	2,31	12,70	60,20	18,60
	4,0	6,90	8,79	45,40	2,27	15,10	72,50	22,00
	5,0	8,42	10,70	53,30	2,23	17,80	86,40	25,70
	6,3	10,30	13,10	61,60	2,17	20,50	102,00	29,60
	7,1	11,40	14,50	65,80	2,13	21,90	110,00	31,60
	8,0	12,50	16,00	69,70	2,09	23,20	118,00	33,40
	10,0	14,90	18,90	75,50	2,00	25,20	131,00	36,00
65	3,0	5,84	7,44	47,64	2,53	14,66	72,94	21,08
	4,0	7,66	9,76	60,46	2,49	18,60	93,24	26,44
	5,0	9,42	12,00	71,88	2,45	22,12	111,60	31,07
	6,3	11,65	14,87	86,06	2,53	26,48	191,31	36,80
	8,0	14,30	18,24	98,37	2,32	30,27	156,00	41,26
	10,0	17,30	22,00	110,20	2,24	33,92	177,10	45,44
70	3,2	6,63	8,44	62,30	2,72	17,80	97,60	26,10
	4,0	8,15	10,40	74,70	2,68	21,30	118,00	31,20
	5,0	9,99	12,70	88,50	2,64	25,30	142,00	36,80
	6,3	12,30	15,60	104,00	2,58	29,70	169,00	42,90
	7,1	13,60	17,30	112,00	2,54	32,00	185,00	46,10
	8,0	15,00	19,20	120,00	2,50	34,20	200,00	49,20
	10,0	18,00	22,90	133,00	2,41	38,00	227,00	54,40
	12,5	21,30	27,10	142,00	2,29	40,60	249,00	58,00
80	3,6	8,53	10,90	105,00	3,11	26,20	164,00	38,50
	4,0	9,41	12,00	114,00	3,09	28,60	180,00	41,90
	5,0	11,60	14,70	137,00	3,05	34,20	217,00	49,80
	6,3	14,20	18,10	162,00	2,99	40,50	262,00	58,70
	7,1	15,80	20,20	176,00	2,95	43,90	286,00	63,50
	8,0	17,50	22,40	189,00	2,91	47,30	312,00	68,30
	10,0	21,10	26,90	214,00	2,82	53,50	360,00	76,80
	11,0	22,80	29,10	223,00	2,77	55,80	380,00	80,10
	12,5	25,20	32,10	234,00	2,70	58,60	404,00	83,80



DIMENSIONAL TABLE



Size b mm	W.T. s mm	Linear mass Kg/m	Cross-section- al area A cm ²	Second moment of area I cm ⁴	Radius of gyration i cm	Elastic section modulus W cm ³	Torsional inertia constant J cm ⁴	Torsional modulus constant C cm ³
90	3,6	9,66	12,30	152,00	3,52	33,80	237,00	49,70
	4,0	10,70	13,60	166,00	3,50	37,00	260,00	54,20
	5,0	13,10	16,70	200,00	3,45	44,40	316,00	64,80
	6,3	16,20	20,70	238,00	3,40	53,00	382,00	77,00
	7,1	18,10	23,00	260,00	3,36	57,70	419,00	83,70
	8,0	20,10	25,60	281,00	3,32	62,60	459,00	90,50
	10,0	24,30	30,90	322,00	3,23	71,60	536,00	103,00
	12,5	29,10	37,10	359,00	3,11	79,80	612,00	114,00
100	4,0	11,90	15,20	232,00	3,91	46,40	361,00	68,20
	5,0	14,70	18,70	279,00	3,86	55,90	439,00	81,80
	6,3	18,20	23,20	336,00	3,80	67,10	534,00	97,80
	7,1	20,30	25,80	367,00	3,77	73,40	589,00	107,00
	8,0	22,60	28,80	400,00	3,73	79,90	646,00	116,00
	10,0	27,40	34,90	462,00	3,64	92,40	761,00	133,00
	11,0	29,70	37,90	488,00	3,59	97,70	812,00	141,00
	12,5	33,00	42,10	522,00	3,52	104,00	879,00	150,00
110	4,0	13,20	16,80	313,00	4,32	56,80	485,00	83,70
	5,0	16,30	20,70	378,00	4,27	68,80	592,00	101,00
	6,3	20,20	25,70	456,00	4,21	83,00	722,00	121,00
	8,0	25,10	32,00	547,00	4,14	99,40	878,00	144,00
	10,0	30,60	38,90	637,00	4,05	116,00	1040,00	168,00
	11,0	33,20	42,30	677,00	4,00	123,00	1110,00	178,00
	12,5	37,00	47,10	728,00	3,93	132,00	1210,00	191,00
	120	3,0	11,00	14,04	320,30	4,78	53,38	485,70
4,0		14,40	18,40	410,00	4,72	68,40	635,00	101,00
5,0		17,80	22,70	498,00	4,68	83,00	777,00	122,00
6,3		22,20	28,20	603,00	4,62	100,00	950,00	147,00
7,1		24,70	31,50	663,00	4,59	110,00	1050,00	161,00
8,0		27,60	35,20	726,00	4,55	121,00	1160,00	176,00
10,0		33,70	42,90	852,00	4,46	142,00	1380,00	206,00
11,0		36,60	46,70	908,00	4,41	151,00	1480,00	219,00
12,5		40,90	52,10	982,00	4,34	164,00	1620,00	236,00